KOOAK PROFESSIONAL Inkjet Photo Paper, Glossy / 255g - Dry Lab

Featuring a true photographic resin-coated base paper, KODAK PROFESSIONAL Inkjet Photo Paper Glossy gives you the freedom to print in your studio, and the KODAK PROFESSIONAL back-print seal of quality to back it up. KODAK PROFESSIONAL Inkjet Photo Paper is compatible with Noritsu, Fuji and Epson Dry Lab printers.

Properties	Specifications
Material	Resin-coated photo base
Gauge	10 mil / 255g
Gloss Level	>/=50
Opacity	>90%
Whiteness	>134
Printer/Ink Compatibility	Compatible with Noritsu, Fuji and Epson Dry Lab printers.
Software Setting	The photo gloss paper setting in most RIPs is appropriate; however, we recommend a custom ICC profile for optimal results. Please refer to www.brandmangagementgroup.com for ICC profiles for some printers.
Light-fastness	The fading time of inkjet ink is a direct result of the inks that you choose to use and the environment where the print is displayed. Contact the ink manufacturer for light-fastness data.
Finishing/Post Processing	It is always recommended that a protective laminate be applied after printing. Hand applying laminate is not recommended. Pressure-sensitive or thermal laminates can be used. Before applying the laminate, allow the image to dry for 24 hours.
Optimal Service Environment	72° F (21° C), 50% R.H For end use: 0-300° F
Handling Recommendations	Due to the absorptive nature of the coating, you should avoid touching the coated surface. It's always recommended that cotton gloves be used when handling inkjet coated materials.
Ideal Storage Conditions	70° F (21° C), 50% R.H. (a controlled environment is recommended); store in original packaging.
Shelf Life	1 year from the BMG ship date when stored in proper conditions.

Product Performance & Suitability: All of the descriptive information and recommendations for the use of Kodak products should be used only as a guide. Furnishing such information and recommendations shall in no event constitute a warranty of any kind by BMG. All Purchasers of Kodak products shall independently determine the suitability of the material for the purpose for which it is purchased. Seller's and manufacturer's only obligation shall be to replace such quantity of the product proved to be defective. Neither the seller nor the manufacturer shall be liable either in the tort in contract for any loss or damage, direct, incidental or consequential (including loss of profits or revenue) arising out of the use of or the inability to use the product. No statement or recommendation not contained herein shall have any force or effect in agreement signed by officers of seller and manufacturer.



